



**Product Name: Bitumen 40/50**

**CAS No.:** 64742-93-4

**HS Code:** 271320

Property	Unit	Typical Value
Penetration @ 25°C	dmm	40 – 50
Softening Point (Ring & Ball)	°C	52 – 60
Flash Point (COC)	°C	> 232
Ductility @ 25°C	cm	> 100
Solubility in Trichloroethylene	%	> 99
Loss on Heating	% wt	< 0.2
Specific Gravity @ 25°C	–	~1.01 – 1.06
Viscosity @ 135°C	cSt	Min. 300
Drop in Penetration after Heating	%	< 20
Appearance	–	Black, Viscous, Shiny
Form	–	Drums / Bulk / Tanker