



Product Name: Bitumen 85/100

CAS No.: 8052-42-4

HS Code: 271320

Property	Unit	Typical Value
Penetration @ 25°C	dmm	85 – 100
Softening Point (Ring & Ball)	°C	42 – 52
Flash Point (COC)	°C	> 230
Ductility @ 25°C	cm	> 100
Solubility in Trichloroethylene	%	> 99
Loss on Heating	% wt	< 0.2
Drop in Penetration after Heating	%	< 20
Viscosity @ 135°C	cSt	Min. 250
Specific Gravity @ 25°C	–	~1.01 – 1.06
Form	–	Viscous, Black, Shiny
Packaging	–	Drums, Jumbo Bags, Bulk