



Product Name: Bitumen Cutback SC-250

CAS No.: 8052-42-4

HS Code: 271410

Property	Typical Value	Test Method
Penetration (25°C, 0.1 mm)	10 – 30	ASTM D5 / EN 1426
Softening Point (°C)	60 – 75	ASTM D36 / EN 1427
Ductility (cm at 25°C)	≥ 40	ASTM D113
Specific Gravity	0.95 – 1.05	ASTM D70
Flash Point (°C)	≥ 35	ASTM D93 (Tag Open Cup)
Viscosity at 25°C (cP)	500 – 2000	ASTM D2170
Solubility in Carbon Disulfide (%)	≥ 99	ASTM D2042
Distillation Residue (%)	≥ 65	ASTM D402