

**Product Name: Bitumen for Waterproofing****CAS No.:** 64742-93-4**HS Code:** 271320

Property	Typical Value	Test Method
Softening Point (°C)	80 – 110	ASTM D36 / EN 1427
Penetration at 25°C (0.1 mm)	10 – 40	ASTM D5 / EN 1426
Specific Gravity @ 25°C	1.00 – 1.10	ASTM D70
Flash Point (°C)	≥ 250	ASTM D92
Ductility at 25°C (cm)	≥ 1	ASTM D113
Loss on Heating (% wt)	≤ 0.5	ASTM D6
Solubility in Trichloroethylene (%)	≥ 99.0	ASTM D2042
Water Absorption (%)	Nil or very low	ASTM D570
Form	Solid, dark brown to black	Visual
Application Temperature (°C)	160 – 200	Manufacturer Spec.