

**Product Name: Oxidized Bitumen 85/35****CAS No.:** 64742-93-4**HS Code:** 27132000

Property	Test Method	Unit	Typical Value
Penetration @ 25°C	ASTM D5	dmm	30 – 40
Softening Point (Ring & Ball)	ASTM D36	°C	85 ± 5
Flash Point (Cleveland Open Cup)	ASTM D92	°C	> 250
Solubility in Trichloroethylene	ASTM D2042	%	≥ 99.0
Loss on Heating	ASTM D6	%	≤ 0.2
Ductility @ 25°C	ASTM D113	cm	< 1.0
Specific Gravity @ 25°C	ASTM D70	g/cm ³	1.00 – 1.10
Ash Content	ASTM D3174	%	< 1.0
Water Content	ASTM D95	%	Nil