Basekim
Chemical Production Co.Ltd.

Product Name: Oxidized Bitumen 75/25

CAS No.: 8052-42-4

HS Code: 271320

Property	Unit	Typical Value
Penetration @ 25°C	dmm	15 – 25
Softening Point (Ring & Ball)	°C	75 ± 5
Flash Point (COC)	°C	> 250
Solubility in Trichloroethylene	%	> 99
Loss on Heating	%	< 0.5
Ductility @ 25°C	cm	< 1
Specific Gravity @ 25°C	–	1.00 – 1.10
Drop Point	°C	180 – 200
Color	–	Black
Form	–	Solid Block / Slab

İLKBAHAR MAH. GALİP ERDEM CD.FAHREDDIN PASA (613) SOKAK, NO.6, ÇANKAYA ANKARA/TURKEY
00903125147074
00903125147081
info@basekim.com
www.basekim.com